

## **COREWELD PRIME MC3 H4**

Seamless metal cored wire for mild steel and 490N/mm<sup>2</sup> class high tensile strength steel. Coreweld Prime MC3 H4 is a metal cored wire that combines the high deposition rates of a rutile slag flux-cored electrode with the high efficiencies of solid wire.

#### **CLASSIFICATIONS WELD METAL**

EN ISO 17632-B	T 49 3 T15 0 M21 A U H5
SFA/AWS A5.18	E70C-6M H4
JIS Z 3313	YFW-A50DM
KS D 7104	YFW-A50DM
EN ISO 17632-A	T 42 3 M M21 3 H5

Shielding Gas	M21 (EN ISO 14175)
Polarity	DC+
Alloy Type	C Mn
Fill Type	Metal Cored
Diff Hydrogen	<4 ml/100g

# TYPICAL ALL WELD METAL ANALYSIS

**Chemical Composition** 

C: 0.12%	Si: 0.90%	Mn: 1.75%	P: 0.03%	S: 0.03%
Cr: 0.20%	Ni: 0.50%	Mo: 0.30%	V: 0.08%	Cu: 0.50%

#### **SPECIFICATIONS**

Diameter (mm)	Current Range (amps)				
	Min	Max	Min	Max	CTWD (mm)
1.2	250	350	31	35	15–20
16	280	390	31	35	15–20

## TYPICAL MECHANICAL PROPERTIES

Using Argon +10 to 25% CO <sub>2</sub>			
Yield Stress	450 MPa		
Tensile Strength	550 MPa		
Elongation	30%		
CVN Impact Values	60J @ -30°C		

#### **FEATURES**

#### MC3 Metal Cored Flux Cored wire

- Seamless wire for guaranteed low hydrogen levels
- No copper coating for lower fume
- ASC coating for rust prevention and outstanding feedability
- High deposition efficiency & deposition rates
- · Vacuumed packed in foil for protection against moisture
- · Precision layered wound
- Grade-3 with a H4 classification.
- It is designed to run on Mixed Argon+CO<sub>2</sub> shielding gases, ranging from 10-25% CO<sub>2</sub>.
- Weld layer transitions in multilayer fillet welds are very smooth and even.
- Spatter levels are very low to extremely low

## **ORDERING INFO**

Part No.	Size	Weight	Description
35MP12247V	1.2mm	15kg	Coreweld Prime MC3 H4
35MP16247V	1.6mm	15kg	Coreweld Prime MC3 H4

## **COREWELD PRIME MC4 H4**

Seamless metal cored wire for mild steel and 490N/mm<sup>2</sup> class high tensile strength steel. Coreweld Prime MC4 H4 is a metal cored wire that combines the high deposition rates of a rutile slag flux-cored electrode with the high efficiencies of solid wire.

### **CLASSIFICATIONS WELD METAL**

EN ISO 17632-B	T 49 4 T15 0 M A U H5
SFA/AWS A5.18	E70C-6M H4
JIS Z 3313	YFW-A50DM
KS D 7104	YFW-A50DM
EN ISO 17632-A	T 42 4 M M21 3 H5

Shielding Gas	M21 (EN ISO 14175)
Polarity	DC+
Alloy Type	C Mn
Fill Type	Metal Cored
Diff Hydrogen	<4ml/100g

# TYPICAL ALL WELD METAL ANALYSIS

#### **Chemical Composition**

C: 0.12%	Si: 0.90%	Mn: 1.75%	P: 0.03%	S: 0.03%
Cr: 0.20%	Ni: 0.50%	Mo: 0.30%	V: 0.08%	Cu: 0.50%

## **SPECIFICATIONS**

Diameter (mm)		t Range ips)		Range lts)	
	Min	Max	Min	Max	CTWD (mm)
1.2	250	350	31	35	15–20
1.6	280	390	31	35	15–20

## TYPICAL MECHANICAL PROPERTIES

Using Argon +10 to 25% CO <sub>2</sub>			
Yield Stress	470 MPa		
Tensile Strength	550 MPa		
Elongation	26%		
CVN Impact Values	60J @ -40°C		

#### **FEATURES**

#### MC4 Metal Cored Flux Cored wire

- Seamless wire for guaranteed low hydrogen levels
- No copper coating for lower fume
- ASC coating for rust prevention and outstanding feedability
- High deposition efficiency & deposition rates
- Vacuumed packed in foil for protection against moisture
- Precision layered wound
- Grade-4 with a H4 classification.
- It is designed to run on Mixed Argon+CO<sub>2</sub> shielding gases, ranging from 10-25% CO<sub>2</sub>.
- Weld layer transitions in multilayer fillet welds are very smooth and even.
- Spatter levels are very low to extremely low

#### **ORDERING INFO**

Part No.	Size	Weight	Description
35MR12247V	1.2mm	15kg	Coreweld Prime MC4 H4
35MR16247V	1.6mm	15kg	Coreweld Prime MC4 H4



# COREWELD PRIME MC3 H4 & MC4 H4 METAL CORED WIRE



