

Purus 46 CF

A non copper coated G4Si1/ER70S-6 solid wire for GMAW of carbon-manganese steels. Purus 46 CF is particularly suited to be used in general construction, automotive components and mobile machinery industries. It has a slightly higher manganese and silicon content than Purus 42 CF to increase the weld metal strength. The wire may be welded with either a gas mixture or with pure CO2 as shielding gas. Purus 46 CF is designed to give a clean weld bead with a minimum of silica islands, low fumes and extremely low spatter levels. The wire is suitable for robotic applications at high deposition rates.

Classifications Weld Metal:	EN ISO 14341-A: G 42 3 C1 4Si1, EN ISO 14341-A: G 46 4 M21 4Si1, EN ISO 14341-A: G 46 4 M20 4Si1
Classifications Wire Electrode:	SFA/AWS A5.18: ER70S-6, EN ISO 14341-A: G 4Si1
Approvals:	CE EN 13479, VdTÜV 19262

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type:	Carbon-manganese steel (Mn/Si-alloyed)		
-------------	--	--	--

Typical Tensile Properti	ypical Tensile Properties			
Condition	Yield Strength	Tensile Strength	Elongation	
AWS CO2 (C1)	AWS CO2 (C1)			
As welded	450 MPa	560 MPa	29 %	
EN 80Ar/20CO2 (M21)				
As welded	475 MPa	585 MPa	26 %	
EN 92Ar/8CO2 (M20)				
As welded	500 MPa	600 MPa	25 %	
EN CO2 (C1)				
As welded	450 MPa	560 MPa	26 %	

Typical Charpy V-Notch Proper	rpy V-Notch Properties		
Condition	Testing Temperature	Impact Value	
AWS CO2 (C1)			
As welded	-30 °C	70 J	
EN 80Ar/20CO2 (M21)			
As welded	20 °C	130 J	
As welded	-30 °C	70 J	
As welded	-40 °C	60 J	
EN 92Ar/8CO2 (M20)			
As welded	-30 °C	90 J	
As welded	-40 °C	80 J	
EN CO2 (C1)			
As welded	20 °C	120 J	
As welded	-30 °C	70 J	



Purus 46 CF

•	pical Wire Composition %		
•	C	Mn	Si
(0.08	1.65	0.90

Deposition Data				
Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.0 mm	80-300 A	18-32 V	2.7-15 m/min	1.0-5.5 kg/h
1.2 mm	120-380 A	18-35 V	2.5-15 m/min	1.3-8.0 kg/h